

FT-2019-0102-01
Producto: Fenólico doble Film

Medida: 1.22 x 2.44 x 18mm

FENOLICO DE GRAN CALIDAD DOBLE FILM

Product		Film faced plywood		Core		Finger Joint Core	
Film		Brown		Film Grammage		220g/m²	
Size		2440*1220*18mm		Glue		WBP Melamine	
NO.	Property		Unit	Standard	Value of Test		Result
1	Moisture Content		%	EN 322	12		pass
2	Average Thickness Tolerance		mm	± 0.5	≤ ± 0.5		pass
3	Glue Bond Strength	Single Test Bond Strength Value	Mpa	EN 314	Max.	1.58	pass
					Min.	0.86	pass
			Average Wood Failure	%	/	80	
4	Bending Strength	Longitudinal	Mpa	EN 310	49.56		pass
		Transverse			36.35		
5	Elastic Modulus	Longitudinal	Mpa		6012		pass
		Transverse			4839		
6	Density		kg/cbm	EN 323	530		pass
7	Cycle Life		5 - 8 reusing times decided by the usage (cleaning and storing after each time using).				

